

PRODUCT DATA



No. 786

MasterFormat:
07 92 13
13 11 00

JANUARY 2026
(Supersedes January 2021)

DECK-O-SEAL® 125 Two-Part Pourable Joint Sealant

DESCRIPTION

DECK-O-SEAL 125 two-part, pourable joint sealant is a self-leveling, polysulfide-based sealing compound. It is a non-staining sealant that cures to a firm, flexible, tear-resistant rubber. DECK-O-SEAL 125 is highly resilient and has excellent recovery characteristics, even after extended periods of compression or elongation. It has outstanding resistance to most chemicals, to all weather conditions, aging, and shrinkage. For on-the-job use, DECK-O-SEAL 125 is supplied in pre-measured 96 oz. (2.84 L) kits consisting of the base compound and a separate container of setting agent. There is enough room in the base container for introduction and mixing of the setting agent. NOTE: DECK-O-SEAL 125 is 25% firmer than regular DECK-O-SEAL.

USES

DECK-O-SEAL 125 is used for horizontal applications. It is ideal for general purpose sealing of joints and seams subjected to high pedestrian or vehicular traffic, such as mall floors or garage floors. DECK-O-SEAL 125 offers high tensile strength and is excellent for joints in swimming pool floors. (Pool floor applications must be primed with REZI-WELD™ LV from W. R. MEADOWS.)

FEATURES/BENEFITS

- Moisture-insensitive.
- Resistant to most chemicals.
- Unitized packaging.
- Long service life.
- Maintenance-free.

PACKAGING

Patented, pre-measured, two-component unitized, easy-to-handle 96 oz. (2.84 L) kit contains proper ratio of base to setting agent, which must be maintained. Included in each kit is the base material, setting agent, stirring paddle and applicator bottle. Four kits are included in each carton.

COVERAGE

(Approximate number of lineal feet that can be sealed with 96-ounce DECK-O-SEAL kit.)

Depth of Joint	WIDTH OF JOINT						
	1/4" (6.4 mm)	3/8" (9.5 mm)	1/2" (12.7 mm)	5/8" (15.9 mm)	3/4" (19.1 mm)	7/8" (22.2 mm)	1" (25.4 mm)
1/4" (6.4 mm)	231 (70.4)	154 (46.9)	106 (32.3)				
3/8" (9.5 mm)		102 (31.1)	77 (23.5)	62 (18.9)	51 (15.5)		
1/2" (12.7 mm)			58 (17.7)	46 (14)	38 (11.5)	33 (10)	29 (8.8)

COLORS

Standard colors include Dura-White, Stone Gray, and Desert Tan. Jet Black and Redwood are available upon special order.

SPECIFICATIONS/STANDARDS

- ASTM C920, Type M, Grade P, Class 25, T and NT
- CRD-C 506, Type I, Classes A & B
- Federal Specifications A-A-1556A, Type M, Grade P, Class 25, T and NT

TECHNICAL DATA*

Shore Hardness	A 30±5
Consistency	Liquid, Self-Leveling
Tack-Free Time	8 Hours
Linear Shrinkage	Negligible
Tensile Strength	125 psi (0.86 MPa)
Elongation	400%+
Peel Adhesion (per ASTM C794) (With primer)	Plate Glass-20 lb./in. (357.2 g/mm) min. Aluminum-20 lb./in. (357.2 g/mm) min.
Application Temperature Range	40° F (4° C) min.
Storage Life	1 year when stored in unopened containers under 80° F (27° C)

*All technical data is typical information, but may vary due to test methods, conditions and operators.

deck-o-seal®

A DIVISION OF W. R. MEADOWS®

CONTINUED ON REVERSE SIDE ...

www.deckoseal.com

P.O. BOX 397 • HAMPSHIRE, IL 60140 • PHONE: 800-542-POOL (7665) • FAX: 847-214-2268

APPLICATION

Follow these instructions carefully for maximum effectiveness. BE SURE TO WEAR PROTECTIVE SAFETY GLASSES AND CHEMICAL-RESISTANT GLOVES.

Surface Preparation ... Remove foreign substances, incompressible, and free water from joint opening. For proper adhesion, joints must be clean and dry. Dust, dirt, and laitance should be removed prior to application. Concrete should be completely cured and free from all foreign materials and contamination from curing agents. (Industry accepted standard for curing concrete is 28 days.) To maintain cleanliness around the joint to be sealed, apply masking tape 2" (51 mm) wide to the surfaces adjoining both sides of the joint before REZI-WELD™ LV and/or DECK-O-SEAL 125 is applied.

Priming ... DECK-O-SEAL 125 adheres well to unprimed concrete; however, REZI-WELD LV is recommended for optimum adhesion. REZI-WELD LV is required for all joints subjected to hydrostatic pressure, submersed under water, and/or for any joint over 1" (25 mm) in width.

Joint Sizes ... Proper joint design practices and application techniques must be followed for successful performance. DECK-O-FOAM®, X-FOAM™, KOOL-ROD™, and KOOL-ROD SOFT from W. R. MEADOWS may be used as a joint backing material to control sealant depth and provide proper joint configuration. For larger joints, use a non-asphalt joint filler, such as CORK EXPANSION JOINT from W. R. MEADOWS, in the joint before sealing.

A 2:1 width-to-depth ratio should be maintained. However, in no case should joint sealant depth be less than 1/4" (6.35 mm) or exceed 1/2" (12.7 mm). DECK-O-SEAL 125 should NOT be used in joints less than 1/4" (6.35 mm) wide.

Mixing ... DECK-O-SEAL 125 is supplied in pre-measured kits with a ratio of setting agent to base, which must be maintained. Store and mix in a cool, shaded area.

Do not mix until ready to use. (Product cannot be re-sealed for future use.)

De-rim both cans with a can opener. Pour the setting agent into the base and mix slowly. To aid in proper mixing, scrape material from the sides and bottom of the container until a uniform color is obtained. **Continue mixing for a recommended 10 minutes, minimum.** A slow-speed drill can be used. Care must be taken to ensure that all setting agent is thoroughly blended with the base component. Avoid trapping air in the sealant.

Application Method ... At 77° F (25° C) and 30% relative humidity, the application life is approximately one hour. Apply thoroughly blended material with supplied squeeze bottle, caulking gun, or any other suitable applicator. Be sure to remove masking tape from both sides of the joint before the sealant starts to set. DECK-O-SEAL 125 will set firm and rubbery within 24 hours at 77° F (25° C). At lower temperatures, curing time may take longer.

Cleanup ... Application equipment should be cleaned promptly with xylene or toluene.

PRECAUTIONS

DECK-O-SEAL 125 is not compatible with asphalt and cannot be used in asphalt concrete pavement or with asphalt-impregnated expansion joint fillers. Note: Do not apply paint over surfaces sealed with DECK-O-SEAL 125. It is strongly recommended that joints under the water line be installed by a professional contractor trained in joint sealing application techniques. Consult with an engineer for proper joint design or waterproofing detail. Homeowners should not attempt these installations.

HEALTH AND SAFETY

Avoid skin contact. If contact should occur, wash affected areas immediately with soap and water. Refer to Safety Data Sheet for complete health and safety information.

For most recent data sheet, sustainability information, and SDS, visit www.deckoseal.com.

LIMITED WARRANTY

"DECK-O-SEAL®, A Division of W. R. MEADOWS, INC., warrants at the time and place we make shipment, our material will be of good quality and will conform with our published specifications in force on the date of acceptance of the order." Read complete warranty. Copy furnished upon request.

Disclaimer

The information contained herein is included for illustrative purposes only, and to the best of our knowledge, is accurate and reliable. DECK-O-SEAL cannot however under any circumstances make any guarantee of results or assume any obligation or liability in connection with the use of this information. As DECK-O-SEAL has no control over the use to which others may put its product, it is recommended that the products be tested to determine if suitable for specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Specifier and user shall determine the suitability of products for specific application and assume all responsibilities in connection therewith.