



MasterFormat: 03 62 13

SEPTEMBER 2014
(Supersedes March 2006)**MEADOW-PLUG™****One Component, Super-Fast Setting, Hydraulic Repair Mortar****DESCRIPTION**

MEADOW-PLUG is a specially blended, extremely fast setting, hydraulic cement product designed to instantly stop running water or fluid seepage in concrete or masonry structures. This single-component, high-strength repair mortar permanently plugs non-moving cracks, joints and voids.

USES

Once mixed with water to a putty-like consistency, MEADOW-PLUG may be hand formed to quickly stop active fluid leaks in basements, tunnels, swimming pools, sewers, non-potable water tanks, voids around pipes, and wall tie holes. It seals construction joints between floors and walls. MEADOW-PLUG is versatile enough for either vertical or horizontal applications; below-, above- or on-grade. Its controlled expansion formulation permanently holds the repair in place on exterior, interior, and even underwater installations.

FEATURES/BENEFITS

- Fast initial set/Stops liquid flow immediately.
- Expands as it sets/Forms a permanent water stop.
- Mixes with water only/Easy to use.
- Horizontal, vertical, interior, exterior/Highly versatile.
- Above grade, below grade, underwater/Multi-purpose.
- Non-metallic, non-corrosive/Will not stain.
- May be top-coated within one hour/Saves time.
- Good sulfate resistance/Suitable for wastewater and sewer applications.

PACKAGING

50 lb. (22.7 kg) Pails
8 lb. (3.6 kg) Tubs

SHELF LIFE

One year from date of manufacture when stored indoors on pallets in a dry, cool area. Do not store product outside.

COVERAGEYield: 0.45 ft.³ (0.012 m³)**Coverage**

	Pail	Tub
3/4" x 3/4" (19 mm x 19 mm)	115 linear feet (35 m)	18 Linear Feet (5.4 m)
1/2" x 1/2" (12.7 mm x 12.7 mm)	259 Linear Feet (78 m)	41 Linear Feet (12.5 m)
1/4" x 1/4" (6.3 mm x 6.3 mm)	1036 Linear Feet (315 m)	165 Linear Feet (50 m)

TECHNICAL DATA**Compressive strength (Per ASTM C 109) at:**

15 min.	850 psi (5.86 MPa)
1 hour	1225 psi (8.44 MPa)
1 day	2650 psi (18.27 MPa)
28 days	6000 psi (41.38 MPa)

Set time (Per ASTM C 191)

Initial: 2 minutes

Final: 3 minutes

All technical data is typical information, but may vary due to testing methods, conditions and operators.

APPLICATION

Surface Preparation ... Cut or notch out the crack, joint, or void to a minimum dimension of 3/4" x 3/4" (19.1 mm x 19.1 mm). To ensure proper mechanical lock, the bottom of the newly notched opening should be wider than the top. (Avoid "V" type notches or cuts.)

Mixing and Placement ... Mix MEADOW-PLUG with enough potable water to form a thick putty consistency (approximately a 4:1 powder-to-water ratio by volume). Do not mix more MEADOW-PLUG than can be placed in one minute. Force MEADOW-PLUG directly into prepared crack and hold in place, maintaining pressure until material hardens. Avoid overworking the material. Just prior to final

CONTINUED ON THE REVERSE SIDE...**W. R. MEADOWS, INC.**

P.O. Box 338 • HAMPSHIRE, IL 60140-0338
Phone: 847/214-2100 • Fax: 847/683-4544
1-800-342-5976
www.wrmeadows.com • info@wrmeadows.com

HAMPSHIRE, IL / CARTERSVILLE, GA / YORK, PA
FORT WORTH, TX / BENICIA, CA / POMONA, CA
GOODYEAR, AZ / MILTON, ON / SHERWOOD PARK, AB

set, MEADOW-PLUG may be “shaved” to match the profile of the area surrounding the patch. If repairing a dry crack, wet cure immediately for at least fifteen minutes or until set is fully achieved. **Do not use on any moving joints.**

PRECAUTIONS

MEADOW-PLUG is recommended for concrete, masonry and block repairs only. Do not apply below 40° F (4° C) or above 90° F (32° C) or when rain is imminent. Protect from freezing for a minimum of 24 hours. Do not bridge moving cracks. Extend existing control and expansion joints through MEADOW-PLUG. Do not add any admixtures. Exceeding liquid requirements shall result in reduced physical properties. Realize that set time will decrease as the product, air, substrate, and mixing liquid temperature increases and will increase as the temperature decreases. Protect from conditions that may cause early water loss: windy conditions, low humidity, high temperature, direct sunlight. Early water loss is exasperated in thin applications. Failure to follow industry standard practices may result in decreased material performance.

LEED INFORMATION

LEED INFORMATION

May help contribute to LEED credits:

- MR Credit 2: Construction Waste Management
- MR Credit 5: Regional Materials

For most recent data sheet, further LEED information, and SDS, visit www.wrmeadows.com.



LIMITED WARRANTY

W. R. MEADOWS, INC. warrants at the time and place we make shipment, our material will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. Read complete warranty. Copy furnished upon request.

Disclaimer

The information contained herein is included for illustrative purposes only, and to the best of our knowledge, is accurate and reliable. W. R. MEADOWS, INC. cannot however under any circumstances make any guarantee of results or assume any obligation or liability in connection with the use of this information. As W. R. MEADOWS, INC. has no control over the use to which others may put its product, it is recommended that the products be tested to determine if suitable for specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Specifier and user shall determine the suitability of products for specific application and assume all responsibilities in connection therewith.